
DEIONIZED WATER
102
104
100
106
FLUORINE COMPOUND
PREMIX SOLUTION PREPARATION
DISPERSION AGENT
FUMED SILICA
202
MIXING
200
DISPERSION
300
AGING
400
GELATION AGENT
502
DEFOAMATION
500
MOLDING
600
GEL AGING
700
DEMOLDING
800
DRYING
900
LOW HEAT TREATMENT
1000
SINTERING
1100

FIG. 1